

## DAFTAR PUSTAKA

- AASHTO T 245-97 (ASTM D 1559-76). Resistance Plastic of Bituminous Mixtures Using Marshall Apparatus. American Society for Testing and Materials.
- Abu N. M. F., Hu X., Lopez Y., Walubita L. F., 1997. Using the fracture energy concept characterize the HMA cracking resistance potential under monotonic crack testing. International journal of pavement research and technology, Vol. 7 No. 1, hal. 40 – 48.
- Affandi F. (2010). Pengaruh Asbuton Semi Ekstraksi Pada Campuran Stone Mastic Asphalt. Bandung : Puslitbang Jalan dan Jembatan.
- Ahmedzade, P., Yilmaz, M., 2008. Effect of polyester resin additive on the propertis of asphalt binders and mixtures. Science Direct, Construction and Building Materials, hal. 481 -486.
- Ahmedzade *et al.* 2007. Effect of polyester resin additive on the propertis of asphalt binders and mixtures. ScienceDirect, Construction and Building Materials, hal. 481- 486
- ASTM D 1559-89. Standard test method for resistance to plastic flow of bituminous mixtures using Marshall Apparatus.
- ASTM D6931 - 12, 2012. Standart test method for indirect tensile (IDT) strength of bituminous mixtures.
- Bell C. A., AbWahab Y., Cristi M.E., & Sosnovske D. (1994). Selection of laboratory aging procedures for asphalt-aggregate mixtures.

Strategic Highway Research Program (SHRP)-A-383. Oregon State University Corvallis, OR 97331.

Birgisson, B., A. Montepara, E. Romeo, R., Roncella, J. A. L., Napier, G., Tebaldi., 2008. Determination and prediction of crack patterns in hot mix asphalt (HMA) mixtures. Science Direct, Construction and Building Materials, hal. 664 -673

Chen J. S. *et al.* 2001. Evaluation of Geosynthetic Applied to Flexible Pavements. Journal of the Eastern Asia Society for Transportation studies, vol.4, No.1,2001.

Chen, Bao-Wen, Kiyoshi Takami, Nobuki Ohmori, and Noboru Harata. (2013) Households Car and Motorcycle Ownership and Transaction Behavior through a Life-Course Approach-a Case in Taipei City. Journal of Eastern Asia Society for Transportation Studies 10.

Croney, D . 1998. The design and performance of road pavements : 3rd edition. New York, NY 10011.

Cullity B. D. 1956. Elements of X-Ray Difrraction. Second Edition : Addison-Wesley Publishing Company Inc.

Departemen Pekerjaan Umum (2006), "Campuran Beraspal Dingin dengan Bahan Peremaja Aspal Emulsi ", Direktorat Jenderal Bina Marga, Jakarta.

Departemen Pekerjaan Umum, Direktorat Jenderal Bina Marga, 2000. Buku 1. Pemanfaatan Asbuton. Umum No : 001-01/BM/2006. Pekerjaan Umum, Direktorat Jenderal Bina Marga, 2006.

- Departemen Pekerjaan Umum. 2006. Buku 1 Pemanfaatan Asbuton Umum. No : 001-01/BM/2006. Direktorat Jenderal Bina Marga.
- Elvik R, Greibe P, 2005, Road Safety effects of porous asphalt : a systematic review of evaluation studies, Elsevier.
- Fultz B. 2013. Transmission Electron Microscopy and Diffractometry of Materials. Springer. ISBN 978-3-642-29761-8.
- Gul. W. A., Guler M., 2014. Rutting susceptibility of asphalt concrete with recycled concrete aggregate using revised Marshall procedure Construction and building materials, 55 hal. 341 – 349
- Huang B. *et al.* 2010. Laboratory evaluation of moisture susceptibility of hot-mix asphalt containing cementitious fillers j. Mater. Civ. Eng. 22:667-673.
- Huang Y. H. 1993. Pavement analysis and design. Englewood Cliffs, NJ 07632.
- Katman H. Y. *et al.* 2012. Tensile strength of reclaimed asphalt pavement. International journal of civil & environmental engineering, Vol. 12 No. 3, hal. 14 - 19
- Khalid H. A. 2002. *A New Approach for The Accelerated Ageing of Porous Asphalt Mixtures*. Proceedings of The Institution of Civil Engineers Liverpool.
- Kliwer J E, Bell C A, Sosnovske D A, 1995, Investigation Of Relationship Between Field Performance And Laboratory Aging Properties Of

Asphalt Mixtures. ASTM STP 1265, American Society For Testing and Materials, Philadelphia.

Kurniadji, (2006), "Asbuton (Aspal Buton) sebagai Bahan Perkerasan Jalan", Pusat Penelitian Jalan dan Jembatan, Bandung.

Mahyuddin A., Tjaronge M. W., Ali N., & Ramli M. I. (2017). Experimental Analysis on Stability and Indirect Tensile Strength in Asphalt Emulsion Mixture Containing Buton Granular Asphalt. International Journal of Applied Engineering Research ISSN 0973-4562 Volume 12, Number 12 (2017).

Maria Isabel Ribeiro "Gaussian Probability Density Function: Properties and Error Characterzation", Book, Institute for System and Robotics Instituto Superior Tcnico 1049-001 Lisboa PORTUGAL,2004.

Nyoman Suaryana. 2008. Penelitian Pemanfaatan Asbuton Butir di Kolaka Sulawesi Tenggara. Pusat Litbang Jalan dan Jembatan.

RSNI T-01-2005 Pengujian Indeks Kepipihan dan Kelonjongan.

Shaowen Du, (2013). Interaction mechanism of cement and asphalt emulsion in asphalt emulsion mixtures. China, Department of Road Engineering, Chang'an University, Xi'an, Shaanxi.

Shu X., Huang B., Vukosavljevic D., 2008. Laboratory evaluation of fatigue characteristics of recycled asphalt mixture. Science Direct, Construction and Building Materials, 22, hal. 1323 -1330.

SNI 03-1968-1990 Pengujian Analisa Saringan Agregat Kasar dan Agregat Halus.

SNI 03-1971-1991 Pengujian Kadar Air Agregat Halus.

SNI 03-2417-1991 Pengujian Keausan Agregat dengan Mesin Abrasi Los Angeles.

SNI 03-2439-1991 Pengujian Kelekatan Agregat terhadap Aspal.

SNI 03-2816-1992 Pengujian Kadar Organik Pasir.

SNI 03-4137-1996. Metode pengujian tebal dan panjang rata-rata agregat

SNI 03-4142-1996. Metode pengujian jumlah bahan dalam agregat yang lolos saringan no. 200 (0,075 mm).

SNI 03-4428-1997 Metode Pengujian Agregat Halus atau Pasir yang Mengandung Bahan Plastik dengan Cara Setara Pasir.

SNI 03-4804-1998 Pengujian Rongga Udara dalam Agregat.

SNI 03-6441-2000 Pengujian Viskositas Aspal Minyak dengan Alat Brookfield Termosel.

SNI 06-2432-1991 Pengujian Daktalitas Aspal.

SNI 06-2433-1991 Pengujian Titik Nyala Aspal.

SNI 06-2433-2011. Pengujian Titik Nyala Dan Titik Bakar Aspal

SNI 06-2434-1991 Pengujian Titik Lembek Aspal.

SNI 06-2438-1991 Pengujian Kelarutan Aspal dalam  $C_2HCl_3$ .

SNI 06-2440-1991 Pengujian Kehilangan Berat Aspal.

SNI 06-2441-1991 Pengujian Berat Jenis Aspal.

SNI 06-2456-1991 Pengujian Penetrasi Aspal.

SNI 06-2489-1991, Metode Pengujian Campuran Aspal Dengan Alat Marshall, Badan Standar Nasional Jakarta.

- SNI 15-7064-2004. Semen Portland komposit
- SNI 1969-2008 Pengujian Berat Jenis dan Penyerapan Agregat Kasar.
- SNI 1970-2008 Pengujian Berat Jenis dan Penyerapan Agregat Halus.
- SNI 2417-2008. Cara Uji keausan agregat dengan mesin abrasi Los Angeles.
- SNI 2432:2011. Cara uji daktilitas Aspal.
- SNI 2432:2011. Cara uji penetrasi aspal
- SNI 2434:2011. Cara uji titik lembek aspal dengan alat cincin dan bola (ring dan ball).
- SNI 2439:2011. Cara uji penyelimutan dan pengelupasan pada campuran agregat aspal.
- SNI 2441:2011. Cara uji berat jenis aspal keras.
- SNI 4798:2011, Spesifikasi Aspal Emulsi Kationik, Badan Standar Nasional Jakarta.
- Spesifikasi Umum Bina marga Divisi 6. (2010). Perkerasan Aspal. Direktorat Jendral Bina marga.
- Suroso Tj. W, 2008, Hubungan Antara Sifat Kimia Aspal dan Sifat Rheologi Aspal. PUSLITBANG PU.
- Suryana A., Inventory on Solid Bitumen Sediment Using 'Outcrop Drilling' in Southern Buton Region, Buton Regency, Province Southeast Sulawesi, Colloquium on Result Activities of Mineral Resources Inventory. - DIM, the TA. 2003, Directorate Mineral (Bandung, in Indonesian) in Tjaronge. M.W and Rita Irmawaty. 2013. Influence of

Water Immersion on Physical Properties of Porous Asphalt Containing Liquid Asbuton as Bituminous Asphalt Binder, Proceedings of 3rd International conference and Sustainable Construction Material and Technologies-SCTM, Kyoto, Japan, 2003, M4-1 e153.

Tayfur S., Ozen H., Aksoy A. 2007. Investigation of rutting performance of asphalt mixtures, containing polymer modifiers. *Sciencedirect* hal. 328– 337.

Tayfur S., Ozen H., Aksoy A., 2005. Investigation of rutting performance of asphalt mixtures containing polymer modifiers. *ScienceDirect, Construction and Building Materials*, hal. 328 -337.

The Shell Bitumen Handbook. (2015). University of Nottingham.

Tjaronge, M.W. and Rita Irmawaty. 2012. Influence of Water Immersion on Physical Properties of Porous Asphalt Containing Liquid Asbuton as Bituminous Asphalt Binder.

VD Mote, Y Purushotham, BN Dole, “Williamson-Hall analysis in estimation of lattice strain in nanometer-sized ZnO particles” in *Journal of Theoretical and Applied Physics* 2012,6:6

Walubita, Lubinda F., Ven, Martin F C van de, 2000. Stresses and Strains in Asphalt-Surfacing Pavements.

Widodo S, Harnaeni SR, Wijayanti E, 2012, Pengaruh Penuaan Aspal Terhadap Karakteristik Asphalt Concrete Wearing Course, UMS.

- Wong W. G., Han H. F., He G. P., Qiu X., Wang K. C. P., Lu W., 2004. Effect of water on permanent deformation potential of asphalt mixture. *Material and structures*, vol. 37, hal. 532 - 538.
- Yamin A Y, Aschuri I, 2008, Pengaruh Penambahan Asbuton pada Penuaan Campuran Aspal, UNDIP.
- Yan J., Ni F., Tao Z. & Jia J. 2009. The Development of Asphalt Emulsion Cold In-Place Recycling Specifications. *Geo Hunan International Conference, Asphalt Material Characterization, Accelerated Testing, and Highway Management*. ASCE.
- Zak, W.H. Abd Majid, M.E Abrishami, Ramin Yousefi. X-Ray Analysis of A. Khorsand ZnO Nanoparticles by Williamson Hall and Size Strain Plot Methods (ScienceDirect) *Solid State Sciences* 13 (2011) 251-256 (2013).
- Zamhari K. A. dkk. 2014. Comparing of Performance of Granular and Extracted Binder From Buton Rock Asphalt. *International Journal of Pavement Research and Technology*. Vol. 7 No.1 Jan 2014.



## **LAMPIRAN**

- 1. Hasil Pengujian Karakteristik Material**
- 2. Rekapitulasi Pengujian Kuat Tarik (*Tensile Strength*)**
- 3. Dokumentasi Penelitian**



### PENURUNAN BERAT ASPAL

Sampel : Aspal Minyak Pen. 60/70  
Metode : SNI 06-2440-1991

No. Sampel	A	B	C	D	E	F	G
	(gram)	(gram)	(gram)	(gram)	(gram)	(gram)	(gram)
1	9.20	84.00	74.80	83.86	74.66	0.14	0.19
2	9.10	86.00	76.90	85.84	76.74	0.16	0.21
Rata-rata							0.20

Keterangan:

- A = Berat tinbox  
B = Berat tinbox + aspal sebelum dioven  
C = Berat aspal sebelum dioven  
D = Berat tinbox + aspal setelah dioven  
E = Berat aspal setelah dioven  
F = Jumlah penurunan berat  
G = % penurunan berat aspal
- $= B - A$   
 $= C - E$   
 $= F/C \times 100\%$

Mengetahui,  
Kepala Laboratorium Ecomaterial

Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.  
NIP. 19680529 200212 1 002



**PENETRASI ASPAL SEBELUM KEHILANGAN BERAT**

Sampel : Aspal Minyak Pen. 60/70  
Metode : SNI 06-2456-1991

Penetrasi Aspal Penurunan 5 Detik	No. Sampel	
	I	II
5	63.00	66.50
5	68.00	65.00
5	64.50	63.00
5	65.00	64.50
5	63.50	67.00
Rata-rata	64.80	65.20
	65.00	

Mengetahui,  
Kepala Laboratorium Ecomaterial

Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.  
NIP. 19680529 200212 1 002



### PENETRASI ASPAL SETELAH KEHILANGAN BERAT

Sampel : Aspal Minyak Pen. 60/70  
Metode : SNI 06-2456-1991

Penetrasi Aspal Penurunan 5 Detik	No. Sampel	
	I	II
5	84.00	80.50
5	81.00	85.00
5	81.50	86.00
5	85.50	83.00
5	80.00	83.50
Rata-rata	82.40	83.60
	83.00	

Mengetahui,  
Kepala Laboratorium Ecomaterial

Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.  
NIP. 19680529 200212 1 002



### DAKTALITAS

Sampel : Aspal Minyak Pen. 60/70  
Berat sampel : 100 gr  
Metode : SNI 06-2432-1991

Pengamatan	Daktalitas pada 25 <sup>0</sup> C, 5 cm per menit
Pengamatan I	110.00
Pengamatan II	109.00
Pengamatan III	111.00
<b>Rata-rata</b>	110.00

Mengetahui,  
Kepala Laboratorium Ecomaterial

Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.  
NIP. 19680529 200212 1 002



### BERAT JENIS ASPAL

Sampel : Aspal Minyak Pen. 60/70  
Metode : SNI 06-2441-1991

No. Sampel	A (gr)	B (gr)	C (gr)	D (gr)	Berat Jenis
1	53.00	110.00	98.00	111.00	1.02
2	53.00	113.00	99.00	113.00	1.00
<b>Rata-rata</b>					1.01

Rumus yang digunakan:

$$BJ = (C - A) / ((B - A) - (D - C))$$

dimana:

- A = Berat piknometer
- B = Berat piknometer + air suling
- C = Berat piknometer + aspal
- D = Berat piknometer + aspal + air suling

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.**  
NIP. 19680529 200212 1 002



**TITIK NYALA ASPAL**

Sampel : Aspal Minyak Pen. 60/70  
Metode : SNI 06-2433-1991

No.	Suhu ( °C )		Waktu ( Detik )	
	I	II	I	II
1	200	200	00 ° 00 ' 00 "	00 ° 00 ' 00 "
2	210	210	00 ° 00 ' 45 "	00 ° 00 ' 37 "
3	220	220	00 ° 01 ' 04 "	00 ° 00 ' 56 "
4	230	230	00 ° 01 ' 45 "	00 ° 01 ' 20 "
5	240	240	00 ° 02 ' 21 "	00 ° 02 ' 05 "
6	250	250	00 ° 02 ' 59 "	00 ° 02 ' 41 "
7	260	260	00 ° 03 ' 29 "	00 ° 03 ' 10 "
8	270	270	00 ° 04 ' 17 "	00 ° 04 ' 20 "
9	280	280	00 ° 05 ' 07 "	00 ° 05 ' 40 "
10	290	290	00 ° 06 ' 15 "	00 ° 06 ' 23 "
11	300	300	00 ° 07 ' 18 "	00 ° 07 ' 18 "
12	310*	310*	00 ° 07 ' 45 "	00 ° 07 ' 46 "
13	320	320	00 ° 08 ' 15 "	00 ° 08 ' 23 "

\* Titik nyala

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.**  
**NIP. 19680529 200212 1 002**



**TITIK LEMBEK ASPAL**

Sampel : Aspal Minyak Pen. 60/70  
Metode : SNI 06-2434-1991

No.	Suhu ( °C )		Waktu ( Detik )	
	I	II	I	II
1	5	5	00 ° 00 ' 00 "	00 ° 00 ' 00 "
2	10	10	00 ° 02 ' 53 "	00 ° 02 ' 53 "
3	15	15	00 ° 09 ' 05 "	00 ° 09 ' 05 "
4	20	20	00 ° 11 ' 11 "	00 ° 11 ' 11 "
5	25	25	00 ° 13 ' 17 "	00 ° 13 ' 17 "
6	30	30	00 ° 16 ' 06 "	00 ° 16 ' 06 "
7	35	35	00 ° 17 ' 25 "	00 ° 17 ' 25 "
8	40	40	00 ° 18 ' 43 "	00 ° 18 ' 43 "
9	45	45	00 ° 21 ' 02 "	00 ° 21 ' 02 "
10	50	50	00 ° 22 ' 26 "	00 ° 22 ' 26 "
11	51*	53*	00 ° 22 ' 52 "	00 ° 23 ' 56 "
Titik lembek ( °C )			51	53
Titik lembek rata-rata ( °C )			52	

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.**  
**NIP. 19680529 200212 1 002**





**BERAT JENIS DAN PENYERAPAN AGREGAT KASAR**

Sampel : Agregat kasar (*chipping* )  
Berat sampel : 2500 gram  
Metode : SNI 03-1969-2008

NO. CONTOH		I	II	Rata-rata
Berat contoh kering oven (gr)	A	2430.00	2406.00	2418.00
Berat contoh kering permukaan (gr)	B	2483.50	2467.00	2475.25
Berat contoh dalam air (gr)	C	1536.00	1519.00	1527.50
Berat jenis bulk (atas dasar kering oven)	$\frac{A}{B - C}$	2.56	2.54	2.55
Berat jenis bulk (atas dasar kering permukaan)	$\frac{B}{B - C}$	2.62	2.60	2.61
Berat jenis semu	$\frac{A}{A - C}$	2.72	2.71	2.72
Penyerapan air	$\frac{B - A}{A} \times 100\%$	2.20	2.54	2.37

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.**  
**NIP. 19680529 200212 1 002**



**BERAT JENIS DAN PENYERAPAN AGREGAT HALUS**

Sampel : Agregat halus (pasir)  
Berat sampel : 500 gram  
Metode : SNI 03-1970-2008

NO. CONTOH		I	II	Rata-rata
Berat contoh kering oven (gr)	A	490.00	491.50	490.75
Berat botol+air sampai batas kalibrasi (gr)	B	754.00	759.00	756.50
Berat contoh+botol+air sampai batas kalibrasi (gr)	C	1064.0	1066.3	1065.15
Berat jenis bulk (atas dasar kering oven)	$\frac{A}{B+500-C}$	2.58	2.55	2.56
Berat jenis bulk (atas dasar kering permukaan)	$\frac{500}{B+500-C}$	2.63	2.59	2.61
Berat jenis semu	$\frac{A}{B+A-C}$	2.72	2.67	2.70
Penyerapan air	$\frac{500-A}{A} \times 100\%$	2.04	1.73	1.89

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tiaronge, ST., M.Eng.**  
**NIP. 19680529 200212 1 002**



**BERAT JENIS DAN PENYERAPAN FILLER**

Sampel : Debu batu (filler)  
Berat sampel : 500 gram  
Metode : SNI 03-1970-2008

NO. CONTOH		I	II	Rata-rata
Berat contoh kering oven (gr)	A	489.40	488.20	488.80
Berat botol+air sampai batas kalibrasi (gr)	B	759.00	757.00	758.00
Berat contoh+botol+air sampai batas kalibrasi (gr)	C	1070.0	1063.0	1066.50
Berat jenis bulk (atas dasar kering oven)	$\frac{A}{B+500-C}$	2.59	2.52	2.55
Berat jenis bulk (atas dasar kering permukaan)	$\frac{500}{B+500-C}$	2.65	2.58	2.61
Berat jenis semu	$\frac{A}{B+A-C}$	2.74	2.68	2.71
Penyerapan air	$\frac{500-A}{A} \times 100\%$	2.17	2.42	2.29

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.**  
NIP. 19680529 200212 1 002



**KEAUSAN AGREGAT DENGAN MESIN LOS ANGELES**

Sampel : Agregat kasar (*chipping*)  
Metode : SNI 03-2417-2008

Gradasi Saringan		No. Sampel	
		I	
Lolos	Tertahan	A	B
		Berat Sebelum (gr)	Berat Sesudah (gr)
3/4"	1/2"	2500	3868
1/2"	3/8"	2500	
Jumlah Berat (gram)		5000	
Berat Tertahan Saringan No. 12 (gram)		3868	
Keausan		$\frac{5000 - 3868}{5000} \times 100\% = 22.64\%$	
Rata - rata		22.64%	

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tiaronge, ST., M.Eng.**  
**NIP. 19680529 200212 1 002**



### INDEKS KEPIPIHAN AGREGAT

Sampel : Agregat kasar (chipping)  
Berat sampel : 1000 gram  
Metode : SNI 03-4137-1996

No.	Gradasi Saringan		Ukuran Thickness Gauge		Berat Lolos Slot (Gram)	Berat Ter-tahan Slot (Gram)	Total Berat (Gram)
			Lebar (mm)	Panjang (mm)			
					I	3/4"	1/2"
II	1/2"	3/8"	4.8	25.4	24.7	475.3	500
Total					82.1	917.9	1000
<b>Indeks Kepipihan</b> = $\frac{\text{Total Berat A}}{\text{Total Berat C}} \times 100\%$					$\frac{82.1}{1000} \times 100\% = 8.21\%$		

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tiaronge, ST., M.Eng.**  
NIP. 19680529 200212 1 002



### KADAR LUMPUR AGREGAT KASAR

Sampel : Agregat kasar (*chipping* )  
Metode : SNI 03-4142-1996

A. Berat kering sebelum dicuci = 1000.00 gram  
B. Berat kering setelah dicuci = 993.40 gram

$$\begin{aligned}\text{Kadar lumpur} &= \frac{A - B}{B} \times 100\% \\ &= \frac{1000.00 - 993.40}{1000.00} \times 100\% \\ &= 0.66\%\end{aligned}$$

Dari hasil percobaan diperoleh kadar lumpur agregat kasar (kerikil) adalah :  
Dik. karakteristik pasir untuk beton harus mempunyai spesifikasi kadar lumpur Maks.1  
sehingga dapat disimpulkan bahwa benda uji material memenuhi standar spesifikasi.

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tiaronge, ST., M.Eng.**  
**NIP. 19680529 200212 1 002**



*SAND EQUIVALENT*

Sampel : Agregat halus (pasir)  
Metode : SNI 03-4428-1997

No.	Uraian	No. Contoh	
		I	II
1	Tera tinggi tangkai penunjuk ke dalam gelas ukur (gelas dalam keadaan kosong).	10.2	10.2
2	Baca skala lumpur. (Pembacaan skala permukaan lumpur dilihat pada dinding gelas ukur).	3.5	3.9
3	Pembacaan skala beban pada gelas ukur (beban dimasukkan pada gelas keadaan kosong).	13.2	13.4
4	Pembacaan skala pasir. (Pembacaan 3 - Pembacaan 1)	3	3.2
5	Nilai Sand Equivalent $\frac{\text{Skala Pasir (4)}}{\text{Skala Lumpur (2)}} \times 100\%$	85.7	82.1
6	Rata-rata nilai Sand Equivalent (%)	83.9	

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.**  
NIP. 19680529 200212 1 002



### ANALISA SARINGAN AGREGAT KASAR

Sampel : Agregat kasar (*chipping* )

Berat sampel : 1500 gram

Metode : SNI 03-1968-1990

No. Saringan	Berat Tertahan (gram)	Kumulatif Tertahan (gram)	Persen Total Tertahan (%)	Persen Lolos (%)
3/4"	0	0	0.00	100.00
1/2"	44.9	44.9	2.99	97.01
3/8"	749.3	794.2	52.95	47.05
4	705.8	1500	100.00	0.00
8	0	1500	100.00	0.00
16	0	1500	100.00	0.00
30	0	1500	100.00	0.00
50	0	1500	100.00	0.00
100	0	1500	100.00	0.00
200	0	1500	100.00	0.00
PAN	0	1500	100.00	0.00

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tjaronge, ST., M.Eng.**  
NIP. 19680529 200212 1 002





### ANALISA SARINGAN AGREGAT HALUS

Sampel : Agregat halus (pasir)  
Berat sampel : 500 gram  
Metode : SNI 03-1968-1990

No. Saringan	Berat Tertahan (gram)	Kumulatif Tertahan (gram)	Persen Total Tertahan (%)	Persen Lolos (%)
3/4"	0	0	0.00	100.00
1/2"	0	0	0.00	100.00
3/8"	0	0	0.00	100.00
4	0	0	0.00	100.00
8	200	200	20.00	80.00
16	0	200	20.00	80.00
30	0	200	20.00	80.00
50	0	200	20.00	80.00
100	0	200	20.00	80.00
200	661.2	861.2	86.12	13.88
PAN	138.8	1000	100.00	0.00

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wibardi Tiaronge, ST., M.Eng.**  
NIP. 19680529 200212 1 002



### ANALISA SARINGAN AGREGAT HALUS

Sampel : Agregat halus (*filler*)

Berat sampel : 1500 gram

Metode : SNI 03-1968-1990

No. Saringan	Berat Tertahan (gram)	Kumulatif Tertahan (gram)	Persen Total Tertahan (%)	Persen Lolos (%)
3/4"	0	0	0.00	100.00
1/2"	0	0	0.00	100.00
3/8"	0	0	0.00	100.00
4	0	0	0.00	100.00
8	400	400	40.00	60.00
16	0	400	40.00	60.00
30	0	400	40.00	60.00
50	0	400	40.00	60.00
100	0	400	40.00	60.00
200	322.4	722.4	72.24	27.76
PAN	277.6	1000	100.00	0.00

Mengetahui,  
Kepala Laboratorium Ecomaterial

**Prof. Dr. H. Muh. Wihardi Tiaronge, ST., M.Eng.**  
NIP. 19680529 200212 1 002

## DOKUMENTASI

### 1. Penyiapan Alat dan Material



Pencucian/pembersihan Agregat



Proses pengeringan agregat



Persiapan Alat Sebelum Pembuatan Benda Uji

## 2. Proses Pembuatan Benda Uji



Proses Pemanasan Agregat dan Aspal Minyak



Proses Pemadatan Campuran Aspal



Proses pengeluaran benda uji dari mould dengan alat *ejector*

### 3. Proses Pengujian Air Laut



#### 4. Proses Pengujian Kuat Tarik



Persiapan Alat Pengujian Kuat Tarik



Proses Pengujian Kuat Tarik



Hasil Pengujian Kuat Tarik

