

DAFTAR PUSTAKA

- Affandi, F., 2008. Karakteristik bitumen asbuton butir pada campuran beraspal panas. *Jurnal jalan – jembatan*, Vol. 25 No. 3, hal. 350 – 368.
- Ahmadinia, Esmaeil, et.al. 2012. Performance Evaluation of Utilization of Waste Polyethylene Terephthalate (PET) in Stone Mastic Asphalt. *Construction and Building Materials, Elsevier*.
- Antara News. 2 Maret, 2018. *Benarkah Jalan Rusak Akibat Tonase Berlebih*.
- Arianti, Nasrul & Balaka, Rudi. 2015. Analisis Pengaruh Penggunaan Polythylene Terephthalate (PET) terhadap Karakteristik Marshall sebagai Bahan Tambah pada Campuran LASTON AC-BC. *Dinamika Jurnal Ilmiah Teknik Mesin*.
- ASTM D1074-09 *Standard Test Method for Compressive Strength of Bituminous Mixtures*.
- Atkins, Harold N, 2003. *Highway Materials, Soil, and Concrete – 4th ed*, Pearson Education Inc., Upper Saddle River, New Jersey.
- Billmeyer, Fred.W.. 1984. *Textbook Of Polymer Science. Third Edition*. John Wiley & Sons, New York.
- Chen J. S. *et al.* 2001. Evaluation of Geosynthetic Applied to Flexible Pavements. *Journal of the Eastern Asia Society for Transportation studies*, vol.4, No.1,2001.

- Croney, D. (1977). "The Design and Performance of Road Pavements. Transport and Road Research Laboratory", London.
- Cullity B. D. 1956. Elements of X-Ray Diffraction. Second Edition : Addison-Wesley Publishing Company Inc.
- Departemen Pekerjaan Umum, Direktorat Jenderal Bina Marga, 2000. Buku 1. Pemanfaatan Asbuton. Umum No : 001-01/BM/2006. Pekerjaan Umum, Direktorat Jenderal Bina Marga, 2006.
- Fultz B. 2013. Transmission Electron Microscopy and Diffractometry of Materials. Springer. ISBN 978-3-642-29761-8.
- Gaus A., Tjaronge M.W., Ali N., & Djamaluddin R. (2015) Compressive strength of asphalt concrete binder course (AC-BC) mixture using Buton Granular Asphalt (BGA). Procedia Engineering, The 5th International Conference of Euro Asia Civil Engineering Forum (EACEF-5), 125: 657-662.
- Hermadi M., Sjahdanulirwan M., 2008. Usulan spesifikasi campuran beraspal panas asbuton Lawele untuk perkerasan jalan. Jurnal jalan– jembatan, Vol. 25 No. 3, hal. 327 - 349
- Huang, baoshan, dkk. 2010. Laboratory evaluation of moisture susceptibility of hot-mix asphalt containing cementitious fillers j. Mater. Civ. Eng. 22:667-673.

- Israil, Djamaluddin, Rudy, & Adisasmita, Sakti A.. 2012. *Studi Pengaruh Plastik sebagai Bahan Substitusi Aspal terhadap Karakteristik Campuran Aspal Beton (AC-WC)*. Tesis tidak diterbitkan. Makassar: Program Pascasarjana Universitas Hasanuddin.
- Jastrzebski, Zbigniew D, 2004. *The Nature and Properties of Engineering Materials*, John Willey & Sons Inc. New York.
- Latifa, Eva Azhra. 2011. *Pengaruh Temperatur dan Pembebanan terhadap Sifat Mekanis Beton Aspal Campuran Panas AC-WC dan HRS*. Tesis tidak diterbitkan. Jakarta: Program Pascasarjana Bidang Ilmu Teknik Universitas Indonesia.
- Mir, Anzar Hamid. 2015. Use of Plastic Waste in Pavement Construction: An Example of Creative Waste Management. *IOSR Journal of Engineering (IOSRJEN)*.
- Moghaddam Taher Baghaee, et.al. 2015. Optimization of Asphalt and Modifier Contents for Polyethylene Terephthalate Modified Asphalt Mixtures Using Response Surface Methodology. *Measurement, Elsevier*.
- Moghaddam, Taher Baghaee, et.al. 2012. Dynamic Properties of Stone Mastic Asphalt Mixtures Containing Waste Plastic Bottles. *Construction and Building Materials, Elsevier*. 34: 236-242.

- Moghaddam, Taher Baghaee, et.al. 2013. Utilization of Waste Plastic Bottles in Asphalt Mixture. *Journal of Engineering Science and Technology*. 8: 264-271.
- Nurminah, Mimi. 2002. *Penelitian Sifat Berbagai Bahan Kemasan Plastik dan Kertas serta Pengaruhnya terhadap Barang yang Dikemas*, Fakultas Pertanian, Jurusan Tekonologi Pertanian, Universitas Sumatera Utara, (Online), (<http://library.usu.ac.id/download/fp/fp-mimi.pdf> diakses 21 Agustus 2016).
- Prasad, K.V.R., et.al. 2015. Use of PET (POLY ETHYLENE TERAPHTALATE) WASTE in Bituminous Road Construction. *International Journal of Emerging Technologies and Engineering (IJETE)*.
- RSNI T-01-2005 Pengujian Indeks Kepipihan dan Kelonjongan.
- Sentosa, Leo. 2012. Analisis Dampak Beban *Overloading* Kendaraan pada Struktur *Rigid Pavement* Terhadap Umur Rencana Perkerasan. *Jurnal Teknik Sipil (Jurnal Teoretis dan Terapan Bidang Rekayasa Sipil)*. 19: 161-168
- SNI 03-1968-1990 Pengujian Analisa Saringan Agregat Kasar dan Agregat Halus.
- SNI 03-1971-1991 Pengujian Kadar Air Agregat Halus.
- SNI 03-2417-1991 Pengujian Keausan Agregat dengan Mesin Abrasi Los Angeles.

SNI 03-2439-1991 Pengujian Kelekatan Agregat terhadap Aspal.

SNI 03-2816-1992 Pengujian Kadar Organik Pasir.

SNI 03-4137-1996. Metode pengujian tebal dan panjang rata-rata agregat

SNI 03-4142-1996. Metode pengujian jumlah bahan dalam agregat yang lolos saringan no. 200 (0,075 mm).

SNI 03-4428-1997 Metode Pengujian Agregat Halus atau Pasir yang Mengandung Bahan Plastik dengan Cara Setara Pasir.

SNI 03-4804-1998 Pengujian Rongga Udara dalam Agregat.

SNI 03-6441-2000 Pengujian Viskositas Aspal Minyak dengan Alat Brookfield Termosel.

SNI 06-2432-1991 Pengujian Daktilitas Aspal.

SNI 06-2433-1991 Pengujian Titik Nyala Aspal.

SNI 06-2433-2011. Pengujian Titik Nyala Dan Titik Bakar Aspal

SNI 06-2434-1991 Pengujian Titik Lembek Aspal.

SNI 06-2438-1991 Pengujian Kelarutan Aspal dalam C_2HCl_3 .

SNI 06-2440-1991 Pengujian Kehilangan Berat Aspal.

SNI 06-2441-1991 Pengujian Berat Jenis Aspal.

SNI 06-2456-1991 Pengujian Penetrasi Aspal.

SNI 06-2489-1991, Metode Pengujian Campuran Aspal Dengan Alat Marshall, Badan Standar Nasional Jakarta.

SNI 15-7064-2004. Semen Portland komposit

SNI 1969-2008 Pengujian Berat Jenis dan Penyerapan Agregat Kasar.

SNI 1970-2008 Pengujian Berat Jenis dan Penyerapan Agregat Halus.

SNI 2417-2008. Cara Uji keausan agregat dengan mesin abrasi Los Angeles.

SNI 2432:2011. Cara uji daktalitas Aspal.

SNI 2432:2011. Cara uji penetrasi aspal

SNI 2434:2011. Cara uji titik lembek aspal dengan alat cincin dan bola (ring dan ball).

SNI 2439:2011. Cara uji penyelimutan dan pengelupasan pada campuran agregat aspal.

SNI 2441:2011. Cara uji berat jenis aspal keras.

Sojobi, Adebayo Olatunbosun, et. al. 2016. Recycling of Polyethylene Terephthalate (PET) Plastic Bottle Wastes in Bituminous Asphaltic Concrete. *Cogent Engineering*.

Soltani, Mehrtash, et.al. 2015. Analysis of Fatigue Properties of Unmodified and Polyethylene Terephthalate Modified Asphalt Mixtures Using Response Surface Methodology. *Engineering Failure Analysis, Elsevier*.

Soyal, Pradeep. 2015. Use of Waste Polyethylene in Bituminous Concrete Mixes. *International Research Journal of Engineering and Technology (IRJET)*.

Spesifikasi Umum Bina marga Divisi 6. (2010). Perkerasan Aspal. Direktorat Jendral Bina marga.

- Starodubsky S., Blechman I., Livneh M., 1994. Stress-strain relationship for asphalt concrete in compression. *Material and structures*, 27, hal. 474 - 482.
- Stephen B., the Shell Bitumen Handbook, University of Nottingham, July 2015
- Sunarya, Yayan. 2011. *Kimia Dasar 2*. Yrama Widya, Bandung.
- Suroso, Tjitjik Wasiah. 2009. Pengaruh Penambahan Plastik LDPE (*Low Density Poly Ethilen*) Cara Basah dan Cara Kering Terhadap Kinerja Campuran Beraspal. *Puslitbang Jalan dan Jembatan*.
- Suroso, Tjitjik Wasiah. 2009. Pengaruh Penambahan Plastik LDPE (*Low Density Poly Ethilen*) Cara Basah dan Cara Kering Terhadap Kinerja Campuran Beraspal. *Puslitbang Jalan dan Jembatan*.
- Syafriana. 2015. Evaluasi Umur Layan Jalan dengan Memperhitungkan Beban Berlebih di Ruas Jalan Lintas Timur Provinsi Aceh. *FSTPT*
- Taherkhani H., Collop A. C., 2008. Determination of the elastic modulus and poisson's ratio of asphaltic mixtures using uniaxial creep recovery tests. *ASCE, Airfield and highway pavements*, hal. 159 - 170.
- Walubita, Lubinda F., Ven, Martin F C van de, 2000. *Stresses and Strains in Asphalt-Surfacing Pavements*.

- Widajat D., Sjahdanulirwan M., 2009. Kinerja daur ulang campuran dingin dengan aspal busa pada lalu lintas berat. *Jurnal jalan – jembatan*, vol. 26, No. 3. Hal 256 – 265.
- Widodo, Sri & Setyaningsih, Ika. 2013. Modulus Elastisitas dan Umur Perkerasan Jalan Beton Aspal sebagai Fungsi Kepadatan. *Eco Rekayasa*.
- Wikipedia. 2016 a. *Plastik*, (Online), (<https://id.wikipedia.org/wiki/Plastik> diakses pada 18 Agustus 2016).

LAMPIRAN

Perbandingan PET dan PP (0 : 100%)

Aspal 6,25%	
Plastik 0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	60,04
3/8 "	136,05
no.4	345,38
no.8	305,06
no.16	224,13
no.30	118,00
no.50	77,40
no.100	72,02
no.200	35,53
Filler	126,39
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 0,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	59,29
3/8 "	135,30
no.4	344,63
no.8	304,31
no.16	223,38
no.30	117,25
no.50	76,65
no.100	71,27
no.200	34,78
Filler	125,64
Plastik PET	0,00
Plastik PP	7,50
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	58,54
3/8 "	134,55
no.4	343,88
no.8	303,56
no.16	222,63
no.30	116,50
no.50	75,90
no.100	70,52
no.200	34,03
Filler	124,89
Plastik PET	0,00
Plastik PP	15,00
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,79
3/8 "	133,80
no.4	343,13
no.8	302,81
no.16	221,88
no.30	115,75
no.50	75,15
no.100	69,77
no.200	33,28
Filler	124,14
Plastik PET	0,00
Plastik PP	22,50
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,04
3/8 "	133,05
no.4	342,38
no.8	302,06
no.16	221,13
no.30	115,00
no.50	74,40
no.100	69,02
no.200	32,53
Filler	123,39
Plastik PET	0,00
Plastik PP	30,00
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2,5 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	56,29
3/8 "	132,30
no.4	341,63
no.8	301,31
no.16	220,38
no.30	114,25
no.50	73,65
no.100	68,27
no.200	31,78
Filler	122,64
Plastik PET	0,00
Plastik PP	37,50
Aspal	100,00
TOTAL	1600,00

Perbandingan PET dan PP (100 : 0%)

Aspal 6,25%	
Plastik 0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	60,04
3/8 "	136,05
no.4	345,38
no.8	305,06
no.16	224,13
no.30	118,00
no.50	77,40
no.100	72,02
no.200	35,53
Filler	126,39
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 0,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	59,29
3/8 "	135,30
no.4	344,63
no.8	304,31
no.16	223,38
no.30	117,25
no.50	76,65
no.100	71,27
no.200	34,78
Filler	125,64
Plastik PP	0,00
Plastik PET	7,50
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	58,54
3/8 "	134,55
no.4	343,88
no.8	303,56
no.16	222,63
no.30	116,50
no.50	75,90
no.100	70,52
no.200	34,03
Filler	124,89
Plastik PP	0,00
Plastik PET	15,00
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,79
3/8 "	133,80
no.4	343,13
no.8	302,81
no.16	221,88
no.30	115,75
no.50	75,15
no.100	69,77
no.200	33,28
Filler	124,14
Plastik PP	0,00
Plastik PET	22,50
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,04
3/8 "	133,05
no.4	342,38
no.8	302,06
no.16	221,13
no.30	115,00
no.50	74,40
no.100	69,02
no.200	32,53
Filler	123,39
Plastik PP	0,00
Plastik PET	30,00
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2,5 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	56,29
3/8 "	132,30
no.4	341,63
no.8	301,31
no.16	220,38
no.30	114,25
no.50	73,65
no.100	68,27
no.200	31,78
Filler	122,64
Plastik PP	0,00
Plastik PET	37,50
Aspal	100,00
TOTAL	1600,00

Perbandingan PET dan PP (25 : 75%)

Aspal 6,25%	
Plastik 0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	60,04
3/8 "	136,05
no.4	345,38
no.8	305,06
no.16	224,13
no.30	118,00
no.50	77,40
no.100	72,02
no.200	35,53
Filler	126,39
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 0,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	59,29
3/8 "	135,30
no.4	344,63
no.8	304,31
no.16	223,38
no.30	117,25
no.50	76,65
no.100	71,27
no.200	34,78
Filler	125,64
Plastik PP (75%)	5,62
Plastik PET (25%)	1,87
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	58,54
3/8 "	134,55
no.4	343,88
no.8	303,56
no.16	222,63
no.30	116,50
no.50	75,90
no.100	70,52
no.200	34,03
Filler	124,89
Plastik PP (75%)	11,25
Plastik PET (25%)	3,75
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,79
3/8 "	133,80
no.4	343,13
no.8	302,81
no.16	221,88
no.30	115,75
no.50	75,15
no.100	69,77
no.200	33,28
Filler	124,14
Plastik PP (75%)	16,87
Plastik PET (25%)	5,62
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,04
3/8 "	133,05
no.4	342,38
no.8	302,06
no.16	221,13
no.30	115,00
no.50	74,40
no.100	69,02
no.200	32,53
Filler	123,39
Plastik PP (75%)	22,50
Plastik PET (25%)	7,50
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2,5 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	56,29
3/8 "	132,30
no.4	341,63
no.8	301,31
no.16	220,38
no.30	114,25
no.50	73,65
no.100	68,27
no.200	31,78
Filler	122,64
Plastik PP (75%)	28,12
Plastik PET (25%)	9,37
Aspal	100,00
TOTAL	1600,00

Perbandingan PET dan PP (75 : 25%)

Aspal 6,25%	
Plastik 0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	60,04
3/8 "	136,05
no.4	345,38
no.8	305,06
no.16	224,13
no.30	118,00
no.50	77,40
no.100	72,02
no.200	35,53
Filler	126,39
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 0,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	59,29
3/8 "	135,30
no.4	344,63
no.8	304,31
no.16	223,38
no.30	117,25
no.50	76,65
no.100	71,27
no.200	34,78
Filler	125,64
Plastik PET (75%)	5,62
Plastik PP (25%)	1,87
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	58,54
3/8 "	134,55
no.4	343,88
no.8	303,56
no.16	222,63
no.30	116,50
no.50	75,90
no.100	70,52
no.200	34,03
Filler	124,89
Plastik PET (75%)	11,25
Plastik PP (25%)	3,75
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,79
3/8 "	133,80
no.4	343,13
no.8	302,81
no.16	221,88
no.30	115,75
no.50	75,15
no.100	69,77
no.200	33,28
Filler	124,14
Plastik PET (75%)	16,87
Plastik PP (25%)	5,62
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,04
3/8 "	133,05
no.4	342,38
no.8	302,06
no.16	221,13
no.30	115,00
no.50	74,40
no.100	69,02
no.200	32,53
Filler	123,39
Plastik PET (75%)	22,50
Plastik PP (25%)	7,50
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2,5 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	56,29
3/8 "	132,30
no.4	341,63
no.8	301,31
no.16	220,38
no.30	114,25
no.50	73,65
no.100	68,27
no.200	31,78
Filler	122,64
Plastik PET (75%)	28,12
Plastik PP (25%)	9,37
Aspal	100,00
TOTAL	1600,00

Perbandingan PET dan PP (50 : 50%)

Aspal 6,25%	
Plastik 0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	60,04
3/8 "	136,05
no.4	345,38
no.8	305,06
no.16	224,13
no.30	118,00
no.50	77,40
no.100	72,02
no.200	35,53
Filler	126,39
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 0,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	59,29
3/8 "	135,30
no.4	344,63
no.8	304,31
no.16	223,38
no.30	117,25
no.50	76,65
no.100	71,27
no.200	34,78
Filler	125,64
Plastik PET (50%)	3,75
Plastik PP (50%)	3,75
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,0%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	58,54
3/8 "	134,55
no.4	343,88
no.8	303,56
no.16	222,63
no.30	116,50
no.50	75,90
no.100	70,52
no.200	34,03
Filler	124,89
Plastik PET (50%)	7,50
Plastik PP (50%)	7,50
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 1,5%	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,79
3/8 "	133,80
no.4	343,13
no.8	302,81
no.16	221,88
no.30	115,75
no.50	75,15
no.100	69,77
no.200	33,28
Filler	124,14
Plastik PET (50%)	11,25
Plastik PP (50%)	11,25
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	57,04
3/8 "	133,05
no.4	342,38
no.8	302,06
no.16	221,13
no.30	115,00
no.50	74,40
no.100	69,02
no.200	32,53
Filler	123,39
Plastik PET (50%)	15,00
Plastik PP (50%)	15,00
Aspal	100,00
TOTAL	1600,00

Aspal 6,25%	
Plastik 2,5 %	
No. Saringan	Berat
3/4 "	0,00
1/2 "	56,29
3/8 "	132,30
no.4	341,63
no.8	301,31
no.16	220,38
no.30	114,25
no.50	73,65
no.100	68,27
no.200	31,78
Filler	122,64
Plastik PET (50%)	18,75
Plastik PP (50%)	18,75
Aspal	100,00
TOTAL	1600,00