

DAFTAR PUSTAKA

- [1] Doremus, R. 1973. Glass Science. Canada:John Wiley and Sons.
- [2] K. Linganna, C.S Rao, and C.K. Jayasankar, 2013, “Optical Properties and Generation of White Light in Dy³⁺-doped lead phosphate glasses”. *J. Quant Spectrosc. Radiat. Transf*, vol 118, pp 40-48, doi.org/10.1016/j.jqsrt.2012.12.002
- [3] J. Kaewkhao, K. Boonin, P. Yasaka, and H. J. Kim, 2015, “Optical and luminescence characteristics of Eu³⁺ doped zinc bismuth borate (ZBB) glasses for red emitting device,” *Mater. Res. Bull.*, vol. 71, pp. 37–41, doi.org/10.1016/j.materresbull.2015.07.002
- [4] J. Kaewkhao, N. Wantana, S. Kaewjaeng, S. Kothan, and H. J. Kim, 2016, “Luminescence characteristics of Dy³⁺ doped Gd₂O₃-CaO-SiO₂-B₂O₃ scintillating glasses,” *J. Rare Earths*, vol. 34, no. 6, pp. 583–589, doi.org/10.1016/S1002-0721(16)60065-0
- [5] R. Vijaya, V. Venkatramu, P. Babu, L. R. Moorthy, and C. K. Jayasankar, 2009, “1.06 μ m laser transition characteristics of Nd³⁺-doped fluorophosphate glasses,” *Mater. Chem. Phys.*, vol. 117, no. 1, pp. 131–137, doi.org/10.1016/j.matchemphys.2009.05.023
- [6] M. Djamal, L. Yuliantini, R. Hidayat, P. Yasaka, K. Boonin, and J.Kaewkhao, 2017, “Optical and Photoluminescence Properties of Dy³⁺ doped ZnO-Al₂O₃-B₂O₃ Glasses for UV Sensor Application,” *J. Technol. Soc. Sci. JTSS*, vol. 1, no. 2, pp. 62–68. doi.org/10.1016/j.matpr.2018.04.069
- [7] P. Meejitpaisan, S. Insiripong, C. Kedkaew, H. J. Kim, and J Kaewkhao, 2017, “Radioluminescence and optical studies of gadolinium calcium phosphate oxyfluoride glasses doped with Sm³⁺,” *Radiat. Phys. Chem.*, vol. 137, pp. 62–67, doi.org/10.1016/j.radphyschem.2016.01.043
- [8] Doremus, R.H. 1994. Glass Science Second Edition. Canada: John Wiley and Sons. Inc
- [9] Kittel, C. 2005. Introduction to Solid State Physics Eight Edition. United States: John Wiley and Sons. Inc
- [10] Shelby, J. E. 2005. Introduction to Glass Science and Technology:2nd

edition. Cornwall: TJ International Ltd

- [11] A. Sharma, S.N Nazrin, S.A. Humaira, I. Boukhria, I. Kebaili, 2022, “Impact of Neodymium Oxide on Optical Properties and X-Ray Shielding Competence of Nd₂O₃-TeO₂-ZnO glasses”. *Radiation Physics and Chemistry*, vol 195, doi.org/10.1016/j.radphyschem.2022.110047
- [12] El-Mallawany, Raouf A.H. 2002. *Tellurite Glasses Handbook (Physical Properties and Data)*. Florida: CRC Press
- [13] D. Snoeck., J. Debo, & N. De Belie, 2020. “Translucent self-healing cementitious materials using glass fibers and superabsorbent polymers” *developments in the Built Environment*, 3, 100012, doi.org/10.1016/j.dibe.2020.100012
- [14] Adryanta. 2008. *Kaca Sebagai Struktur Pada Bangunan*. Skripsi. Universitas Indonesia. Depok.
- [15] Ngo, T.D., 2020. Introduction to composite materials. *Composite and Nanocomposite Materials—From Knowledge to Industrial Applications*.
- [16] M. Hasanuzzaman, A. Rafferty, M. Sajjia, & A. -G Olabi. 2016. “Properties of Glass Materials”. *Reference Module in Materials Science and Materials Engineering*. doi:10.1016/b978-0-12-803581-8.03998-9
- [17] N. Chanthima, J. Kaewkhao, and P. Limsuwan, “Study of photon interactions and shielding properties of silicate glasses containing Bi₂O₃, BaO and PbO in the energy region of 1 keV to 100 GeV,” *Ann. Nucl. Energy*, vol. 41, pp. 119–124, Mar. 2012, doi.org/10.1016/j.anucene.2011.10.021
- [18] M.G. Dong, M.I. Sayyed, G. Lakshminarayana, M. Çelikbilek Ersundu, A.E. Ersundu, P. Nayar, M.A. Mahdi, “Investigation of gamma radiation shielding properties of lithium zinc bismuth borate glasses using XCOM program and MCNP5 code,” *J. Non-Cryst. Solids*, vol. 468, pp. 12–16, Jul. 2017, doi.org/10.1016/j.jnoncrysol.2017.04.018
- [19] M. H. Kharita, R. Jabra, S. Yousef, and T. Samaan, “Shielding properties of lead and barium phosphate glasses,” *Radiat. Phys. Chem.*, vol. 81, no. 10, pp. 1568–1571, Oct. 2012, doi.org/10.1016/j.radphyschem.2012.05.002
- [20] K. Boonin, P. Yasaka, P. Limkitjaroenporn, R. Rajaramakrishna, A. Askin,

- M.I Sayyed, S. Kothan, J. Kaewkhao, “Effect of BaO on lead free zinc barium tellurite glass for radiation shielding materials in nuclear application” *J. Non-Cryst. Solids*, Vol. 550, pp. 1 – 7, August.2020, doi.org/10.1016/j.jnoncrysol.2020.120386
- [21] N. Luewarasirikul, H. J. Kim, P. Meejitpaisan, and J. Kaewkhao, 2017 “White light emission of dysprosium doped lanthanum calcium phosphate oxide and oxyfluoride glasses,” *Optical. Materials.*, vol. 66, pp. 559–566,. doi.org/10.1016/j.optmat.2017.02.049
- [22] Agustino, R. 2010. Fabrikasi dan Studi Komposisi Kaca Posfat. Skripsi. Semarang: FMIPA Universitas Negeri Semarang
- [23] K. Jolley and R. Smith, 2016. “Radiation tolerance of iron phosphate: A study of amorphous and crystalline structures” *Journal of Nuclear Materials*, 479, pp.347-356, doi.org/10.1016/j.jnucmat.2016.07.028
- [24] Setiawan H, 2003. Laporan Orientasi kerja PT. IGLAS. Departemen Pengendalian Mutu Produksi:Gresik.
- [25] Abbas A, 1985. Sifat-sifat Gelas Padat. LIPI, Bandung
- [26] Astuti, Budi, 2005. Pembuatan dan Uji Kekerasan Gelas pada Sistem Gelas P_2O_5 - SM_2O_3 - MNO_2 . Jurusan Fisika UNS, Semarang
- [27] Z. P. Lu, C. T. Liu and W. D. Porter. 2003. Role of Yttrium in glass formation of Fe-based bulk metallic glasses, 83(13):2581-2583, doi.org/10.1063/1.1614833
- [28] Mubarok AT, 2019. Variasi Suhu Annealing pada Sintesis $CoFe_2O_4$ dari Pasir Besi Sungai Bengawan Solo. [Skripsi]. Surakarta: Universitas Sebelas Maret Surakarta.
- [29] A. Bunaciu, E.G Udriștioiu,; H.Y Aboul-Enein, 2015. “X-Ray Diffraction: Instrumentation and Application”. *Critical Reviews in Analytical Chemistry*, 45(4), 289–299, doi.org/10.1080/10408347.2014.949616
- [30] Munasir, et all. 2012 “Uji XRD dan XRF pada Bahan Mineral (Batuan dan Pasir) sebagai Sumber Material Cerdas ($CaCO_3$ dan SiO_2)”.*Jurnal Penelitian Fisika dan Aplikasinya (JPFA)*, Vol 2 No. 1. Hal 24-25. Surabaya
- [31] M. R. Nasrabadi, M. Behpour, A.S. Nasab, M.R. Jeddy, 2016, “Nanocrystalline Ce Doped Copper Ferrite:Synthesis, Characterization, And

- Its Photocatalyst Application”, *J Mater Sci: Mater Electron.* 27, 11691-11697, doi.org/10.1007/s10854-016-5305-8
- [32] J. Revathi, M. J Abel, V. Archana, T. Sumithra, R. Thiruneelakan dan, J Joseph Prince, 2020, “Synthesis and Characterization of CoFe₂O₄ and Ni-Doped CoFe₂O₄ Nanoparticles By Chemical Co-Precipitation Technique For Photo Degradation Of Organic Dyestuffs Under Direct Sunlight”, *Physica B: Physics Of Condensed Matter*, 587, 412136, doi.org/10.1016/j.physb.2020.412136
- [33] A. Kalam, A.G Al-Schemi, M Assiri, G.Du, T. Ahmad, I. Ahmad, M. Pannipara, 2018, “Modified Solvothermal Synthesis of Cobalt Ferrite (CoFe₂O₄) Magnetic Nanoparticles Photocatalysts For Degradation of Methylene Blue With H₂O₂/Visible Light”, *Result In Physics.* 8 1046-105, doi.org/10.1016/j.rinp.2018.01.045
- [34] Singh, S., Kalia, G., & Singh, K. (2015). Effect of intermediate oxide (Y₂O₃) on thermal, structural and optical properties of lithium borosilicate glasses. *Journal of Molecular Structure*, 1086, 239–245. doi:10.1016/j.molstruc.2015.01.031
- [35] Kh. S. Shaaban,(2021), Tuning the Crystallization Behavior B₂O₃ -SiO₂ – Bi₂O₃ – TiO₂ – Y₂O₃ Glasses, Chemistry Department, Faculty of Science, Al-Azhar University, : <https://doi.org/10.21203/rs.3.rs-346000/v1>
- [36] Fayad, A. M., Abd-Allah, W. M., & Moustafa, F. A. (2017). *Effect of Gamma Irradiation on Structural and Optical Investigations of Borosilicate Glass Doped Yttrium Oxide. Silicon*, 10(3), 799–809. doi:10.1007/s12633-016-9533-6
- [37] Mohini, G. J., Krishnamacharyulu, N., Sahaya Baskaran, G., Rao, P. V., & Veeraiah, N. (2013). Studies on influence of aluminium ions on the bioactivity of B₂O₃–SiO₂–P₂O₅–Na₂O–CaO glass system by means of spectroscopic studies. *Applied Surface Science*, 287, 46–53. doi:10.1016/j.apsusc.2013.09.055
- [38] Afrizal, N. H., Yahya, N., Yusoff, N. M., Kasim, A., & Hashim, A. (2020). Physical, Mechanical and Structural Properties of Yttrium Oxide

- Doped Zinc Borate Glasses. *Solid State Phenomena*, 307, 327–335. doi:10.4028/www.scientific.net/ssp.307.327
- [39] Zhang, L., Li, Z., Zhen, F., Wang, L., Zhang, Q., Sun, R., ... Chen, H. (2017). High sinterability nano-Y₂O₃ powders prepared via decomposition of hydroxyl-carbonate precursors for transparent ceramics. *Journal of Materials Science*, 52(14), 8556–8567. doi:10.1007/s10853-017-1071-0
- [40] Misbah, M. H., Abdelghany, A. M., El-Agawany, F. I., Rammah, Y. S., & El-Mallawany, R. (2021). On Y₂O₃·Li₂O·Al₂O₃·B₂O₃ glasses: synthesis, structure, physical, optical characteristics and gamma-ray shielding behavior. *Journal of Materials Science: Materials in Electronics*, 32(12), 16242–16254. doi:10.1007/s10854-021-06172-2
- [41] Reddy, A. P., Rao, P. N., Reddy, M. C. S., Rao, B. A., & Veeraiiah, N. (2020). Second harmonic generation and spectroscopic characteristics of TiO₂ doped Li₂O–Al₂O₃–B₂O₃ glass matrix. *Applied Physics A*, 126(9). doi:10.1007/s00339-020-03879-7
- [42] Kaur, G., Kumar, M., Arora, A., Pandey, O. P., & Singh, K. (2011). Influence of Y₂O₃ on structural and optical properties of SiO₂–BaO–ZnO–xB₂O₃–(10–x) Y₂O₃ glasses and glass ceramics. *Journal of Non-Crystalline Solids*, 357(3), 858–863. doi:10.1016/j.jnoncrysol.2010.11.103
- [43] Alatawi, A., Alsharari, A. M., Issa, S. A. M., Rashad, M., Darwish, A. A. A., Saddeek, Y. B., & Tekin, H. O. (2020). Improvement of mechanical properties and radiation shielding performance of AlBiBO₃ glasses using yttria: An experimental investigation. *Ceramics International*, 46(3), 3534–3542. doi:10.1016/j.ceramint.2019.10.069
- [44] W.A.W. Razali, K. H., (2012). Effect of Li₂O on the Physical Properties of Nd₂O₃ Doped Tellurite Glass. *Solid state science and Technology*, 20 (1-2), 121-127.
- [45] Mardhiah Abdullah, W.M., (2015). The Physical Properties of Lead Borate (PbO-B₂O₃) Glass. 380-386.

- [46] Bayya, S.S., Harbison, B.B., Sanghera, J.S., and Aggarwal, I.D., (1997). BaO-Ga₂O₃-GeO₂ glasses with enhanced properties. *Journal of Non-Crystalline Solids*, 212, 198-207.
- [47] Buijnsters, J. G., Vázquez, I. & Ter Meulen, J. J. 2009. Substrate pretreatment by ultrasonication with diamond powder mixtures for nucleation enhancement in diamond film growth. *Diamond and related materials*, 18, 1239-1246.

LAMPIRAN

Lampiran 1. Prosedur Penelitian

Preparasi Sampel



Lampiran 2. Analisis Data

Tabel 1. Hasil pengambilan data Vicker's Hardness (HV) 3 titik pengujian sampel kaca borat silika

Y2O3 (mol %)	Vicker's Hardness (HV)	Average
0	367.6	375.3
	374.2	
	384	
5	404.4	402.1
	408.9	
	393.1	
10	403.1	404.1
	403.1	
	406.1	
15	459.9	446.5
	424.3	
	455.2	
20	414.2	407.4
	403.7	
	404.4	