

## DAFTAR PUSTAKA

- Abbe, O. and Hamilton, L. (2017) *BRE Global Environmental Weighting for Construction Products using Selected Parameters from EN 15804*, Book. Available at: [https://files.bregroup.com/bre-co-uk-file-library-copy/filelibrary/Materials/Environmental-weightings-15804\\_final.pdf](https://files.bregroup.com/bre-co-uk-file-library-copy/filelibrary/Materials/Environmental-weightings-15804_final.pdf) (Accessed: 17 December 2023).
- Adamu, M. *et al.* (2021) ‘Mechanical performance and optimization of high-volume fly ash concrete containing plastic wastes and graphene nanoplatelets using response surface methodology’, *Construction and Building Materials*, 308(October). Available at: <https://doi.org/10.1016/j.conbuildmat.2021.125085>.
- Ai-Tayyib, A., Ai-Zahrani, M. and Al-Sulaimani, G. (1988) *Effect of polypropylene fiber reinforcement on the properties of fresh and hardened concrete in the Arabian Gulf environment*, *CEMENT and CONCRETE RESEARCH*. Available at: [https://doi.org/https://doi.org/10.1016/0008-8846\(88\)90049-X](https://doi.org/https://doi.org/10.1016/0008-8846(88)90049-X).
- Almeshal, I. *et al.* (2020) ‘Eco-friendly concrete containing recycled plastic as partial replacement for sand’, *Journal of Materials Research and Technology*, 9(3), pp. 4631–4643. Available at: <https://doi.org/10.1016/j.jmrt.2020.02.090>.
- Alqahtani, F.K. *et al.* (2016) ‘Production of Recycled Plastic Aggregates and Its Utilization in Concrete’, *Journal of Materials in Civil Engineering*, 29(4). Available at: [https://doi.org/https://doi.org/10.1061/\(ASCE\)MT.1943-5533.000176](https://doi.org/https://doi.org/10.1061/(ASCE)MT.1943-5533.000176).
- Arabyarmohammadi, H., Sharbatdar, M.K. and Naderpour, H. (2023) ‘Experimental Investigation of Mix Proportions Effects on Roller-Compacted Concrete Properties Using Response Surface Methodology’, *International Journal of Pavement Research and Technology*, 16(4), pp. 1021–1046. Available at: <https://doi.org/10.1007/s42947-022-00177-8>.
- Asbhy, M.F. and Jones, D.R.H. (1988) *Engineering Materials 2*. Cambridge: Pergamon.
- Attanasio, A. *et al.* (2015) ‘Sustainable aggregates from secondary materials for innovative lightweight concrete products’, *Heron*, 60(1–2), pp. 5–25.
- Batikha, M. *et al.* (2021) ‘Using recycled coarse aggregate and ceramic waste to produce sustainable economic concrete’, *International Journal of Sustainable Engineering*, 14(4), pp. 785–799. Available at: <https://doi.org/10.1080/19397038.2020.1862353>.
- BSN (2011) ‘Standarisasi Nasional Indonesia 03 - 4431 - 2011 : Cara uji kuat lentur kuat lentur beton normal dengan dua dengan dua titik pembebanan’. Available at: [www.bsn.go.id](http://www.bsn.go.id).
- Chen, C. *et al.* (2010) ‘LCA allocation procedure used as an incitative method for

- waste recycling: An application to mineral additions in concrete', *Resources, Conservation and Recycling*, 54(12), pp. 1231–1240. Available at: <https://doi.org/10.1016/j.resconrec.2010.04.001>.
- Choi, Y.W. *et al.* (2005) 'Effects of waste PET bottles aggregate on the properties of concrete', *Cement and Concrete Research*, 35(4), pp. 776–781. Available at: <https://doi.org/10.1016/j.cemconres.2004.05.014>.
- Choi, Y.W. *et al.* (2009) 'Characteristics of mortar and concrete containing fine aggregate manufactured from recycled waste polyethylene terephthalate bottles', *Construction and Building Materials*, 23(8), pp. 2829–2835. Available at: <https://doi.org/10.1016/j.conbuildmat.2009.02.036>.
- Dawood, A.O., AL-Khazraji, H. and Falih, R.S. (2021) 'Physical and mechanical properties of concrete containing PET wastes as a partial replacement for fine aggregates', *Case Studies in Construction Materials*, 14, p. e00482. Available at: <https://doi.org/10.1016/j.cscm.2020.e00482>.
- Departemen Permukiman Dan Prasarana Wilayah (2003) *Pd T-14-2003 Perencanaan Perkerasan Jalan Beton Semen, Book*. Jakarta: Departemen Permukiman dan Prasarana Wilayah. Available at: <https://pu.go.id/pustaka/biblio/pd-t-14-2003-perencanaan-perkerasan-jalan-beton-semen/3LB9B> (Accessed: 12 January 2024).
- Dhawan, R. *et al.* (2019) 'Recycling of plastic waste into tiles with reduced flammability and improved tensile strength', *Process Safety and Environmental Protection*, 124, pp. 299–307. Available at: <https://doi.org/10.1016/j.psep.2019.02.018>.
- Donatello, S., Tyrer, M. and Cheeseman, C.R. (2010) 'Comparison of test methods to assess pozzolanic activity', *Cement and Concrete Composites*, 32(2), pp. 121–127. Available at: <https://doi.org/10.1016/j.cemconcomp.2009.10.008>.
- Eřtokov, A., Wolfov Fabinov, M. and Ondov, M. (2022) 'Concrete Structures and Their Impacts on Climate Change and Water and Raw Material Resource Depletion', *International Journal of Civil Engineering*, 20(6), pp. 735–747. Available at: <https://doi.org/10.1007/s40999-022-00701-8>.
- European Standard (2000) *European Standard ENV 197-1, European Standard*. Available at: <https://webstore.ansi.org/standards/bsi/bsen1972000#:~:text=BS EN 197-1%3A2000 Cement. Composition%2C specifications and conformity,27 distinct common cement products and their constituents.>
- Frigione, M. (2010) 'Recycling of PET bottles as fine aggregate in concrete', *Waste Management*, 30(6), pp. 1101–1106. Available at: <https://doi.org/10.1016/j.wasman.2010.01.030>.
- Galve, J.E. *et al.* (2022) 'Life Cycle Assessment of a Plastic Part Injected with Recycled Polypropylene: A Comparison with Alternative Virgin Materials', *International Journal of Precision Engineering and Manufacturing - Green Technology*, 9(3), pp. 919–932. Available at:

- <https://doi.org/10.1007/s40684-021-00363-2>.
- Gartner, E. (2012) 'Are there any practical alternatives to the manufacture of portland cement clinker?', *Kuei Suan Jen Hsueh Pao/Journal of the Chinese Ceramic Society*, pp. 61–68. Available at: <https://doi.org/10.14062/j.issn.0454-5648.2012.01.019>.
- Hama, S.M. and Hilal, N.N. (2017) 'Fresh properties of self-compacting concrete with plastic waste as partial replacement of sand', *International Journal of Sustainable Built Environment*, 6(2), pp. 299–308. Available at: <https://doi.org/10.1016/j.ijsbe.2017.01.001>.
- Hamdi, F. *et al.* (2021) *Teknologi Beton Indonesia*. CV. Tohar Media.
- Hussein, H.H., Abd Al-Ameer, O. and Ahmed, M.K. (2016) 'Use fine PVC waste to improve acoustic and thermal insulation of concrete', (November 2016). Institut Bauen und Umwelt e.V. (IBU) (2021) 'EPD-EFC-20210198-IBG1-EN Environmental Product Declaration Concrete admixtures - Plasticizer and superplasticizer. 2021.' Available at: [https://cdnmedia.mapei.com/docs/librariesprovider39/products-documents/7\\_epd-efca-2021-for-plasticizers-and-superplasticizers\\_e5ab3bfaa3324a828e8edcb6d51198b8.pdf?sfvrsn=b628a495\\_0](https://cdnmedia.mapei.com/docs/librariesprovider39/products-documents/7_epd-efca-2021-for-plasticizers-and-superplasticizers_e5ab3bfaa3324a828e8edcb6d51198b8.pdf?sfvrsn=b628a495_0).
- Institut für Energie- und Umweltforschung Heidelberg (2017) *EcoProfile of Polyolefins (HDPE and PP)*. Available at: <https://www.ifeu.de/en/project/oekoprofil-von-polyolefinen-aus-laendern-des-mittleren-ostens/>.
- International Atomic Energy Agency (2002) 'Guidebook on non-destructive testing of concrete structures', *Industrial Applications and Chemistry Section, IAEA*, 17(17), p. 231. Available at: [http://200.10.161.33/cirsoc/pdf/ensayos/tcs-17\\_web.pdf](http://200.10.161.33/cirsoc/pdf/ensayos/tcs-17_web.pdf).
- Islam, M.J. and Shahjalal, M. (2021) 'Effect of polypropylene plastic on concrete properties as a partial replacement of stone and brick aggregate', *Case Studies in Construction Materials*, 15(July), p. e00627. Available at: <https://doi.org/10.1016/j.cscm.2021.e00627>.
- Kim, T., Tae, S. and Chae, C.U. (2016) 'Analysis of environmental impact for concrete using LCA by varying the recycling components, the compressive strength and the admixture material mixing', *Sustainability (Switzerland)*, 8(4), pp. 1–14. Available at: <https://doi.org/10.3390/su8040389>.
- Kim, T., Tae, S. and Roh, S. (2013) 'Assessment of the CO<sub>2</sub> emission and cost reduction performance of a low-carbon-emission concrete mix design using an optimal mix design system', *Renewable and Sustainable Energy Reviews*, 25, pp. 729–741. Available at: <https://doi.org/10.1016/j.rser.2013.05.013>.
- Kim, T.H. and Chae, C.U. (2016) 'Environmental impact analysis of acidification and eutrophication due to emissions from the production of concrete', *Sustainability (Switzerland)*, 8(6), pp. 1–20. Available at:

- <https://doi.org/10.3390/su8060578>.
- Majhi, R.K. and Nayak, A.N. (2020) 'Production of sustainable concrete utilising high-volume blast furnace slag and recycled aggregate with lime activator', *Journal of Cleaner Production*, 255. Available at: <https://doi.org/10.1016/j.jclepro.2020.120188>.
- Margarida, A. *et al.* (2015) *Impacte ambiental comparado do ciclo de vida de betão com agregados grossos reciclados e naturais Engenharia Civil*. Instituto Superior Técnico. Available at: <https://fenix.tecnico.ulisboa.pt/cursos/mec/dissertacao/846778572210846>.
- Meshram, R.B. and Kumar, S. (2022) 'Comparative life cycle assessment (LCA) of geopolymer cement manufacturing with Portland cement in Indian context', *International Journal of Environmental Science and Technology*, 19(6), pp. 4791–4802. Available at: <https://doi.org/10.1007/s13762-021-03336-9>.
- Needhidasan, S. and Sai, P. (2020) 'Demonstration on the limited substitution of coarse aggregate with the E-waste plastics in high strength concrete', *Materials Today: Proceedings*, 22, pp. 1004–1009. Available at: <https://doi.org/10.1016/j.matpr.2019.11.255>.
- Neville, A.M. (1995) *Properties of Concrete*. 4th edn. Prentice Hall.
- Ohemeng, E.A. and Naghizadeh, A. (2023) 'Alternative cleaner production of masonry mortar from fly ash and waste concrete powder', *Construction and Building Materials*, 374. Available at: <https://doi.org/10.1016/j.conbuildmat.2023.130859>.
- Olofinnade, O., Chandra, S. and Chakraborty, P. (2020) 'Recycling of high impact polystyrene and low-density polyethylene plastic wastes in lightweight based concrete for sustainable construction', *Materials Today: Proceedings*, 38, pp. 2151–2156. Available at: <https://doi.org/10.1016/j.matpr.2020.05.176>.
- Ozturk, E. *et al.* (2022) 'Factors affecting the CO<sub>2</sub> emissions, cost efficiency and eco-strength efficiency of concrete containing rice husk ash: A database study', *Construction and Building Materials*, 326(November 2021), p. 126905. Available at: <https://doi.org/10.1016/j.conbuildmat.2022.126905>.
- PlasticEurope (2022) 'Plastics – the Facts 2022', *Plastic Europe*, (October), pp. 1–81. Available at: <https://plasticseurope.org/knowledge-hub/plastics-the-facts-2022/>.
- Pourkhorshidi, A.R. *et al.* (2010) 'Applicability of the standard specifications of ASTM C618 for evaluation of natural pozzolans', *Cement and Concrete Composites*, 32(10), pp. 794–800. Available at: <https://doi.org/10.1016/j.cemconcomp.2010.08.007>.
- Rajesh Varma, N. and Chekravarthy, D. (2022) 'An experimentation made on plastic and demolished waste in concrete mix', *Materials Today: Proceedings*, 62, pp. 3473–3478. Available at: <https://doi.org/10.1016/j.matpr.2022.04.298>.

- Sachdeva, N., Shrivastava, N. and Shrivastava, S. (2023) ‘Pozzolanic reaction and strength activity index of dolomite powder incorporated cement mortar’, *Materials Today: Proceedings* [Preprint]. Available at: <https://doi.org/10.1016/j.matpr.2023.05.042>.
- Safi, B. *et al.* (2013) ‘The use of plastic waste as fine aggregate in the self-compacting mortars: Effect on physical and mechanical properties’, *Construction and Building Materials*, 43, pp. 436–442. Available at: <https://doi.org/10.1016/j.conbuildmat.2013.02.049>.
- Samadi, M. *et al.* (2020) ‘Waste ceramic as low cost and eco-friendly materials in the production of sustainable mortars’, *Journal of Cleaner Production*, 266, p. 121825. Available at: <https://doi.org/10.1016/j.jclepro.2020.121825>.
- Shinkhede, S. *et al.* (2021) ‘Comparison of different concrete compositions based on sustainability score’, *International Journal of Sustainable Engineering*, 14(6), pp. 2048–2059. Available at: <https://doi.org/10.1080/19397038.2021.1966123>.
- Siddique, R., Khatib, J. and Kaur, I. (2008) ‘Use of recycled plastic in concrete: A review’, *Waste Management*, 28(10), pp. 1835–1852. Available at: <https://doi.org/10.1016/j.wasman.2007.09.011>.
- Sistem Informasi Pengelolaan Sampah Nasional (SIPSN) (2022) *Capaian Kinerja Pengelolaan Sampah, Kementerian Lingkungan Hidup dan Kehutanan*. Available at: <https://sipsn.menlhk.go.id/sipsn/> (Accessed: 5 December 2023).
- SNI 03-2847:2002 (2002) *Perhitungan struktur beton untuk bangunan gedung*. Jakarta.
- SNI 03-6861.1-2002 (2002) *Spesifikasi Bahan Bangunan*. Jakarta: Badan Standardisasi Nasional.
- SNI 2847:2019 (2019) *Persyaratan beton struktural untuk bangunan gedung dan penjelasan*. Jakarta: Badan Standardisasi Nasional.
- SNI 7064:2014 (2004) *Semen Portland Komposit*, Badan Standardisasi Nasional. Jakarta: Badan Standardisasi Nasional. Available at: [https://binamarga.pu.go.id/otomasi9/index.php?p=show\\_detail&id=23559&keywords=](https://binamarga.pu.go.id/otomasi9/index.php?p=show_detail&id=23559&keywords=).
- Thwe, E., Khatiwada, D. and Gasparatos, A. (2021) ‘Life cycle assessment of a cement plant in Naypyitaw, Myanmar’, *Cleaner Environmental Systems*, 2, p. 100007. Available at: <https://doi.org/10.1016/J.CESYS.2020.100007>.
- Vembu, P.R.S. and Ammasi, A.K. (2023) ‘Eco-Efficiency Evaluation of Sustainable Self-Compacting Concrete Using Magnesite Mine Waste’, *Case Studies in Construction Materials* [Preprint]. Available at: <https://doi.org/https://doi.org/10.1016/j.cscm.2023.e02765>.
- Wałach, D. *et al.* (2019) ‘Environmental performance of ordinary and new generation concrete structures—a comparative analysis’, *Environmental Science and Pollution Research*, 26(4), pp. 3980–3990. Available at:


<https://doi.org/10.1007/s11356-018-3804-2>.

Wang, C.-K. and XSalmon, C.G. (1993) *Reinforced Concrete Design (Disain Beton Bertulang)*. 4th edn. Jakarta: Erlangga.

World Bank (2021) 'Plastic Waste Discharges from Rivers and Coastlines in Indonesia', *Plastic Waste Discharges from Rivers and Coastlines in Indonesia* [Preprint]. Available at: <https://doi.org/10.1596/35607>.

# LAMPIRAN

	<b>Universitas Hasanuddin</b>	<b>Nama : Jenrisari D. B</b>
	<b>Program Studi Magister Teknik Sipil</b>	<b>NIM : D012222010</b>
<b>LAMPIRAN</b>		<b>Tgl Percobaan : Februari 2024</b>

<p>Persiapan material</p>	
<p>Pengujian karakteristik material</p>	

	Universitas Hasanuddin	Nama : Jenrisari D. B
	Program Studi Magister Teknik Sipil	NIM : D012222010
LAMPIRAN		Tgl Percobaan : Maret 2024

Pencampuran material menggunakan *mixer*.

1. Pertama, batu pecah, pasir, semen, dan pelet PP dimasukkan ke dalam *mixer* dan dicampur selama 60 detik.



2. Selanjutnya, air yang telah dicampur dengan SP ditambahkan secara bertahap ke dalam *mixer*, dan pencampuran dilanjutkan selama 120 detik.



	Universitas Hasanuddin	Nama : Jenrisari D. B
	Program Studi Magister Teknik Sipil	NIM : D012222010
LAMPIRAN		Tgl Percobaan : Maret 2024

3. Kemudian, campuran beton diaduk secara manual agar bahan – bahan yang menempel pada bagian bawah dan dinding *mixer* tercampur rata.



4. Pencampuran menggunakan *mixer* dilanjutkan selam 60 detik hingga didapatkan kombinasi campuran beton segar yang merata




Pengujian slump beton sesuai target nilai desain slump.



	<b>Universitas Hasanuddin</b>	<b>Nama : Jenrisari D. B</b>
	<b>Program Studi Magister Teknik Sipil</b>	<b>NIM : D012222010</b>
<b>LAMPIRAN</b>		<b>Tgl Percobaan : Maret 2024</b>

<p>Memasukkan campuran ke ke dalam cetakan balok dengan dimensi <math>40 \times 10 \times 10</math> cm, lalu dipadatkan selama 60 detik menggunakan mesin vibrator.</p>	
<p>Proses perawatan benda uji dicurring menggunakan air pada suhu ruang selama 28 hari.</p>	
<p>Pengujian kuat lentur beton</p>	

	<b>Universitas Hasanuddin</b>	<b>Nama : Jenrisari D. B</b>
	<b>Program Studi Magister Teknik Sipil</b>	<b>NIM : D012222010</b>
<b>LAMPIRAN</b>		<b>Tgl Percobaan : Maret 2024</b>

<p>Pengujian <i>ultrasonic pulse velocity</i> (UPV)</p>	
<p>Hasil beton yang telah diuji</p>	