

DAFTAR PUSTAKA

- Darusman L K. 2001. *Diktat Kimia Analitik 1 jilid 1*. Bogor: Departemen Kimia FMIPA-IPB.
- Devenport. 2002. *Extractive Metallurgy of Activated Minerals Fourth Edition*. Kidlington England
- Dominy, Simon C., dkk. 2018. *Integrating the theory of sampling into underground mine grade control strategies*
- E. Rusmana, K. Parris, U. Sukanta dan H. Samodra. 1995. *Geologi Lembar Timika*. Bandung. Pusat Penelitian dan Pengembangan Geologi.
- Faeyumi. 2012. *Sebaran Potensi Emas Epitermal Di Areal Eksplorasi PT. Antam Unit Geomin, Tbk Kecamatan Nanggung Kabupaten Bogor*. Depok: Universitas Indonesia.
- Freeport-McMoran. 2022, *Technical Report Summary of Mineral Reserves and Mineral Resources for Grasberg minerals district*. Papua Indonesia
- Habashi, fathi. 1997. *Handbook of Etractive Metallurgy. Volume 1* weinheim, Germany : A Wiley Company.
- Hidayat, T., Fadhilah dan Nasra, E., 2014. *Penentuan Kadar Perak (Ag) Dalam Batuan Termineralisasi Menggunakan Metode Ekstraksi Pelarut Kelat Ditizon Dengan variasi Ph dan Waktu di Wilayah Tambang Galian Rakyat Bukit Gunjo Jorong Tanjung Bunga Kec. Bonjol Kab. Pasaman*. Padang : Universitas Negeri Padang
- Horath, L. 2001. *Fundamental of Materials for Technologist : Properties, Testing and Laboratory Exercises, 2nd Edition*. New Jersey: Prentice Hall
- Hunt et al. 2011. *A Special Issue Dedicated to Geometallurgy*. Peru: Pontifical Catholic University
- ISO 12743 : 2006. *Copper, Lead, Zinc and Nickel Concentrates-Sampling Procedures For Determination of Metal and Moisture Content*
- Junaedy. 2016. *Studi Zona Mineralisasi Emas Menggunakan Metode Magnetik di Lokasi Tambang Emas Poboya*. Palu: Universitas Tadulako

- Julian Fajri. 2018. *Sistem pengendalian kualitas (Quality Control) pada proses fabrikasi project refinery development master plan (RDMP)*. Karawang: Universitas singaperbangsa karawang.
- Khopkar S.M. 1990. *Konsep Dasar Kimia Analitik*, diterjemahkan oleh Saptorahardjo dan Agus Nurhadi, Jakarta: Universitas Indonesia Press.
- P. F. Indonesia. *Chapter 5 Ore Processing*.
- P. F. Indonesia. *Sekilas Tentang Kami* PT. Freeport Indonesia, [Online]. Available:<https://ptfi.co.id/id/overview>. [Accessed 17 03 2024].
- P. F. Indonesia. *Sejarah Kami*. PT. Freeport Indonesia, [Online]. Available: <https://ptfi.co.id/id/sejarah-kami>. [Accessed 17 03 2024].
- Regina. 2008. *Titration Iodometry*. Yogyakarta: Universitas Negeri Yogyakarta
- Rukihati. 2003. *Perbandingan NAA dengan ICP-MS untuk analisis unsur kelumit dalam berbagai jenis bahan*. Tangerang : Puslitbang Iptek.
- Rukihati. 2006. *Analisis Cuplikan Lingkungan dan Bahan Geologi dengan Inductively Coupled Plasma-Mass Spectrometry*. Tangerang: Pusat Teknologi Bahan Industri Nuklir
- Santoso. 2011. *Analisis Kadar Emas pada Sampel Konsentrat dan Cupel Loss Menggunakan Metode Fire Assay Secara Gravimetri dan Spektrofotometri Serapan Atom*. Yogyakarta: Universitas Islam Indonesia
- Supriadidjaja, A. 2007. *Penentuan Kadar Emas (Au) Dan Perak (Ag) Metode Fire Assay: Perbandingan Hasil Analisis Peleburan Tungku Gas Terhadap Tungku Solar*. *Jurnal Riset Geologi & Pertambangan*. 1 (1): 51-59.
- Ufford, A.I.Q. 1996. *Stratigraphy, Structural Geology, and Tectonics of Young Forearc-Continent Collision, Western Central Range, Irian Jaya (western New Guinea), Indonesia*. Austin: Universitas Texas
- Victor, Lishchuk. 2015. *The Geometallurgical Framework, Malmberget and Mikheevskoye Case Studies*. Mining Science: Universitas Wroclaw
- Zhou, J. 2013. *Gold Geometallurgy And Its Application*. *Gold Sci. Technol.* 21 (5): 76-80

L

A

M

P

I

R

A

N



Analytical Report

Jl. Kuala Kuningan, Kav-D1 Light
Industrial Park, Kuala Kencana.
Timika-Papua Tengah. 99968
Telp: (0901)301947
301222
301949

Final Report Frame

Job No : TMK.B01.00349.2024

Date received: 19-Feb-24

Date reported: 23-Feb-24

Client name: PT. FREEPORT INDONESIA

Order number: BIAS TES SAMPLE B1-B15

Sample ID	Au1	Au2	Cu	Ag
SAMPLE B1	19.27	19.62	26.68	78.6
SAMPLE B2	19.93	19.23	26.71	78.5
SAMPLE B3	20.22	19.82	26.80	78.7
SAMPLE B4	20.06	20.76	26.93	76.2
SAMPLE B5	18.97	19.69	26.99	75.2
SAMPLE B6	19.58	20.50	26.98	78.0
SAMPLE B7	19.58	19.72	26.11	77.3
SAMPLE B8	19.82	19.38	26.90	75.1
SAMPLE B9	20.06	20.17	27.01	75.0
SAMPLE B10	19.95	19.97	26.91	75.8
SAMPLE B11	19.59	19.98	27.01	76.5
SAMPLE B12	19.71	19.90	26.94	74.6
SAMPLE B13	17.06	17.44	26.99	77.0
SAMPLE B14	17.27	17.84	26.91	76.8
SAMPLE B15	18.90	18.38	27.02	75.9

Scheme	FAS7DG	FAS7DG	M016TIT	GOG1AAS
Unit	PPM	PPM	%	PPM
Lower DL	5	5	0.1	0.5
Upper Limit	300	300	50	100

Approved By: _Fajar_
Kabid Inspeksi & Pengujian



Analytical Report

Jl. Kuala Kuningan, Kav-D1 Light
Industrial Park, Kuala Kencana.
Timika-Papua Tengah. 99968
Telp: (0901)301947
301222
301949

Final Report Autocutter

Job No : TMK.B01.00348.2024
Date received: 19-Feb-24
Date reported: 23-Feb-24
Client name: PT. FREEPORT INDONESIA
Order number: BIAS TES SAMPLE A1-A15

Sample ID	Au1	Au2	Cu	Ag
SAMPLE A1	19.43	19.11	26.59	81.7
SAMPLE A2	20.06	19.25	26.37	83.0
SAMPLE A3	19.50	20.29	26.70	81.6
SAMPLE A4	21.21	20.50	25.92	85.6
SAMPLE A5	20.16	19.65	26.84	80.9
SAMPLE A6	20.19	20.13	26.49	84.4
SAMPLE A7	19.20	19.13	26.80	81.1
SAMPLE A8	19.44	20.19	26.73	80.7
SAMPLE A9	20.27	19.98	26.74	82.5
SAMPLE A10	19.73	20.69	27.00	83.0
SAMPLE A11	20.92	20.12	26.64	81.9
SAMPLE A12	20.62	19.86	26.71	83.1
SAMPLE A13	17.31	17.57	26.72	80.5
SAMPLE A14	16.95	17.09	26.84	80.2
SAMPLE A15	18.61	18.29	26.81	80.0

Scheme	FAS7DG	FAS7DG	M016TIT	GOG1AAS
Unit	PPM	PPM	%	PPM
Lower DL	5	5	0.1	0.5
Upper Limit	300	300	50	100

Approved By: _Fajar_
Kabid Inspeksi & Pengujian



Analytical Report

Jl. Kuala Kuningan, Kav-D1 Light
Industrial Park, Kuala Kencana,
Timika-Papua Tengah. 99968
Telp: (0901)301947
301222
301949

Final Report Grab

Job No : TMK.B01.00350.2024

Date received: 19-Feb-24

Date reported: 26-Feb-24

Client name: PT. FREEPORT INDONESIA

Order number: BIAS TES SAMPLE C1-C15

Sample ID	Au1	Au2	Cu	Ag
SAMPLE C1	19.79	19.40	26.13	81.2
SAMPLE C2	18.18	18.56	26.93	80.1
SAMPLE C3	17.49	17.74	27.04	77.5
SAMPLE C4	19.69	20.18	26.85	79.1
SAMPLE C5	19.85	20.10	27.18	80.0
SAMPLE C6	19.66	19.48	27.06	79.8
SAMPLE C7	19.73	19.56	27.08	77.7
SAMPLE C8	19.57	19.34	27.04	76.5
SAMPLE C9	18.31	19.25	27.15	78.7
SAMPLE C10	19.61	19.55	27.06	79.2
SAMPLE C11	19.16	19.40	26.99	77.9
SAMPLE C12	19.04	19.37	27.22	77.1
SAMPLE C13	19.03	18.86	26.88	76.0
SAMPLE C14	19.00	19.22	27.09	77.2
SAMPLE C15	19.36	19.43	26.98	75.7

Scheme	FAS7DG	FAS7DG	M016TIT	GOG1AAS
Unit	PPM	PPM	%	PPM
Lower DL	5	5	0.1	0.5
Upper Limit	300	300	50	100

Page 2 of 3

Approved By: _Fajar_
Kabid Inspeksi & Pengujian